

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁶ : C08F 2/22, C08L 101/02, C09D 5/02	A1	(11) International Publication Number: WO 97/38020 (43) International Publication Date: 16 October 1997 (16.10.97)
(21) International Application Number: PCT/US97/05900 (22) International Filing Date: 10 April 1997 (10.04.97) (30) Priority Data: 08/629,894 10 April 1996 (10.04.96) US (71) Applicant: HEHR INTERNATIONAL INC. [US/US]; 3333 Casitas Avenue, Los Angeles, CA 90039 (US). (72) Inventor: SMITH, Stuart, B.; 2069 Christian Circle, Conyers, GA 30208 (US). (74) Agent: CROWLEY, Richard, P.; 901 Main Street, P.O. Box 901, Osterville, MA 02655-0901 (US).		(81) Designated States: AU, CA, JP, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>With amended claims and statement.</i>

(54) Title: MODIFIED ACRYLIC URETHANE PREPOLYMER CONCENTRATE AND POLYESTER RESINS CONTAINING SAME**(57) Abstract**

A modified acrylic urethane prepolymer composition and an unsaturated polyester resin composition to which the prepolymer has been added. The prepolymer composition includes an acrylic urethane prepolymer prepared by the reaction of diisocyanate, like MDI, with a hydroxyl-containing acrylate monomer, such as a pentaerythritol triacrylate, which prepolymer composition may contain a styrene monomer and an inhibitor, such as benzoquinone, to retard the reaction of the prepolymer and styrene monomer prior to the addition of the prepolymer composition into the polyester resin composition. The employment of the modified urethane prepolymer composition provides for the reduction in the amount of styrene monomer used in the unsaturated resin composition and also provides for improved chemical and physical properties of the cured, unsaturated resin composition, such as a reduction in glass roll-out when the resin composition is employed with fiberglass.

SN 10/069020

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon	KR	Republic of Korea	PL	Poland		
CN	China	KZ	Kazakhstan	PT	Portugal		
CU	Cuba	LC	Saint Lucia	RO	Romania		
CZ	Czech Republic	LI	Liechtenstein	RU	Russian Federation		
DE	Germany	LK	Sri Lanka	SD	Sudan		
DK	Denmark	LR	Liberia	SE	Sweden		
EE	Estonia			SG	Singapore		

DESCRIPTION

Modified Acrylic Urethane Prepolymer Concentrate
and Polyester Resins Containing SameBackground of the Invention

5 Polyester resins are polycondensation products of a dicarboxylic acid with dihydroxy alcohols. Such polyester resins catalyze to cure or harden, generally at room temperatures, to make a wide variety of products. Unsaturated polyester resins are widely used today to make
10 products for use in the marine, transportation and building industries, and in particular, fiber or particulate reinforced products, such as glass fiber reinforced laminate-type products. Unsaturated polyester resins generally contain ethylenic unsaturation introduced by the
15 employment of unsaturated diacids, thus comprising thermosetting-type resins. As such, unsaturated resins generally employ maleic and fumaric unsaturated acids, although saturated acids, phthalic and adipic acid may also be included to control or reduce the amount of unsaturation
20 in the final unsaturated polyester resin and to control the physical properties. Dihydroxy alcohols most generally used are typically ethylene, propylene, di-ethylene and dipropylene glycols. Cross linking agents may be employed with the unsaturated polyester resins. Generally, styrene
25 monomers and di-allyl phthalate are the most common cross linking agents. The styrene monomers are used to reduce the viscosity of the polyester resin and to act also as a cross linker in the polyester resins.

It is desirable, particularly in view of the toxicity
30 of the styrene monomer and government regulations, to reduce the concentration levels of the styrene monomer from the usual 40% to 50% by weight of the polyester resin to below 35% or 30% by weight. However, reductions in styrene monomer concentrations present problems in the polyester
35 resins with the increased viscosity of the resin causing difficulties in applying the resins, such as causing spray

problems and glass roll-out when the resin is sprayed or used in conjunction with glass fibers. The reduced styrene monomer polyester resin does not wet the glass in preparing glass fiber laminates, and therefore, the surface of the sprayed glass fiber polyester resin typically must be contacted with a roller to prevent glass fibers from sticking out of the surface. In addition, the physical properties of the styrene monomer-reduced polyester resins are also greatly reduced without the use of additional, supplemental cross linkers in the polyester resin. The aromatic nature of styrene monomers in the unsaturated polyols improves the hydrolytic stability and increases the chemical resistance to water, detergents and corrosion in the final, cured polyester resin product.

Acrylic monomers, such as methyl methacrylate (MMA) have been added to low or reduced styrene monomer polyester resins for marine grade gel coats and for outdoor applications. However, and unfortunately, MMA has a strong odor, is a skin and eye irritant and results in a slowing of the cure rate of a polyester resin. However, such acrylic monomers usually improve UV, water and chemical resistance. Therefore, it is not desirable to substitute MMA monomer for the styrene monomer or to add it with the styrene monomer, since MMA is also a hazardous material.

It is therefore desirable to provide new and improved, cross linkable diluent compositions to replace or reduce styrene monomer in unsaturated resins, to provide unsaturated, cured resins with better physical and chemical properties and to provide an unsaturated polyester resin composition having reduced styrene monomer therein.

Summary of the Invention

The invention relates to a modified acrylic urethane prepolymer concentrate for use with unsaturated polyester resins and to the unsaturated polyester resin compositions containing the concentrate as a diluent and a cross linking composition and to the cured unsaturated polyester resin

compositions and their uses in the method of preparing laminates and resin products.

The invention concerns an improved, liquid modified acrylic urethane prepolymer concentrate adapted for addition to unsaturated polyester resin compositions to provide improved cured resin properties and to provide unsaturated polyester resin compositions of reduced styrene monomer content. The liquid concentration comprises a modified acrylic urethane prepolymer or oligomer prepared by the reaction of a polyisocyanate, such as an aromatic isocyanate, like MDI, or an aliphatic isocyanate, usually in a stoichiometric amount or in a slight excess, with an hydroxyl-containing acrylate monomer with or without the presence of a catalyst and a diluent monomer, like a styrene monomer, generally in an amount of less than 40% by weight of the unsaturated polyester resin composition to which the concentrate is added, and an inhibitor, such as quinone compound, such as benzoquinone, to retard any prereaction of the prepolymer and the styrene monomer in the concentrate.

The invention is also concerned with unsaturated resin compositions subject to curing in the presence of a catalyst, typically a peroxide alone or with a metal promoter, like a metal carboxylate, such as a cobalt or copper salt, alone or in combination with various accelerators, which are amine or amide accelerators. The catalytic amount of the peroxide compound added just prior to use of the resin composition is usually accompanied with or the resin composition contains a promoting amount of a metal promoter salt at room temperatures in order to provide sufficient exothermic heat to cure the unsaturated polyester resin composition containing the concentrate. An unsaturated polyester resin composition is usually employed either alone or typically in conjunction with filler material, such as particles or fiber materials, like clay, quartz, sand, limestone, mica, pigments or fibers, like glass fibers, or combinations in amounts of about 0% to 30% by weight of the resin in order to prepare cured laminates

of the unsaturated polyester resin, such as a spray laminate, containing glass fibers admixed with the polyester resin.

It has been discovered that the replacement or
5 reduction in amount of a styrene monomer as a diluent and cross linking additive to unsaturated polyester resin compositions may be accomplished by employment of modified acrylic urethane prepolymers which result in improved
10 properties to the cured polyester, better handling in preparing laminates as regards roll-out of the laminate and permits reduction of the styrene monomer, typically to amounts lower than 40%, for example from 0% to 30% by weight of the polyester resin composition. Particularly, it
15 has been discovered that higher functionality acrylic monomers improve the polyester properties of the cured polyester composition. When a polyisocyanate, like MDI, is added to unsaturated polyester resin compositions by itself, such MDI tends to react with the hydroxyl group unsaturated
20 polyester resin composition leading to increased and high viscosity which greatly reduces the feasibility of employing the unsaturated polyester resin composition as a diluent additive. Employment of a MMA monomer itself provides certain disadvantages. Therefore, the employment of a
25 modified acrylic urethane prepolymer, a liquid concentrate, either alone or together with a styrene monomer and an inhibitor, may be used as a diluent additive to unsaturated polyester resin compositions to improve properties and to prepare compositions of reduced styrene monomer content.

In particular, it has been discovered that the high
30 functionality aliphatic urethane prepolymers provide for a variety of improved cure properties of a polyester resin as set forth, for example, in Table I.

Properties	Mono	Di	Tri	Tetra	Penta
------------	------	----	-----	-------	-------

	Cure Speed	Slow→ → → → → → → → → → → → → → Fast
	Flexibility	High← ← ← ← ← ← ← ← ← ← ← ← ← ← Low
5	Hardness	Low→ → → → → → → → → → → → → → High
	Solvent Resistance	Low→ → → → → → → → → → → → → → High
	Crosslink Density	Low→ → → → → → → → → → → → → → High

The employment of a special hydroxyl containing high functionality acrylic monomer, that is, an acrylic monomer with hydroxyl groups, being made into a prepolymer by the employment of a polyisocyanate, either aromatic or aliphatic diisocyanate, and which prepolymer so prepared in a preferred embodiment remains in a liquid condition. This liquid concentrate can be added to the low level styrene monomer unsaturated polyester resin compositions and produce a stable polyester resin composition, which does not react unless and until the peroxide catalysts or a catalyst-accelerator promoter combination is added to the unsaturated polyester resin composition. The addition of the catalytic curing composition, such as the use of methyl ethyl ketone peroxide as one example, provides for rapid cure of the polyester without significant loss of unreacted styrene monomer, so that the resulting unsaturated polyester resin with the liquid concentrate wets glass fiber with excellent efficiency and significantly reduces the need to roll-out the glass, where the unsaturated polyester resin composition is sprayed with glass fibers to form a glass fiber reinforced laminate.

The concentrate includes in one example an hydroxyl alkyl, such C₂-C₆ acrylic monomer which is reacted with a diisocyanate to provide the modified acrylic urethane prepolymer for use in the concentrate. Low functionality acrylic monomers, while not the preferred embodiment, provide for improved cure, chemical and physical properties of the polyester resin, since such low functionality modified acrylic urethane prepolymers with the low functionality used therein provide for solidified prepolymers or prepolymers which rapidly gel, and a liquid

concentrate is the preferred embodiment. Some representative types of the acrylic monomers useful in the invention would include 2-hydroxy ethyl acrylate; hydroxy propyl acrylate; 2-hydroxy ethyl methacrylate; 2-hydroxy ethyl propyl methacrylate; and acrylic urethane prepolymers made from having an 100 index down to a 20 index with solidification occurring in most prepolymers, except for the prepolymers having a 20 or below index.

A preferred acrylic polymer which provides for a liquid concentrate comprises a pentaerythritol acrylate composed of tri-, tetra- and pentacrylate, which acrylic monomer has an hydroxyl group or an active hydrogen for reaction with the diisocyanate. Reaction of this pentaerythritol polyacrylate with diisocyanate, such as MDI, at different levels produces a stable liquid prepolymer, which does not react when added to an unsaturated polyester resin prior to the peroxide agent addition to the promoted unsaturated resin. For example, with a pentaerythritol triacrylate made up of tetra- and pentacrylate, the molecular weight of the acrylic monomer is 298 with a hydroxyl number of 298, which is reacted with MDI with 32% NCO and a 2.3 functionality with the MDI containing both 4-4 and 2-4 isomers.

Other high functionality hydroxyl acrylic monomers suitable for use would include ethoxylated or propoxylated trimethylol propane or glycerol polyacrylate, e.g., tri acrylate monomers. Specific high functionality acrylic monomers suitable for use include ethoxylated trimethylol propane triacrylate; pentaerythritol tri, tetra and pentacrylate, propoxylated trimethylolpropane triacrylate; propoxylated glycerol triacrylate; di-tri methylol propane tetracrylate; dipentaerythritol pentacrylate; and ethoxylated pentaerythritol tetracrylate and combinations thereof.

The prepolymer is made by reacting with or without a catalyst the hydroxyl-containing acrylic monomer with polyisocyanate, more particularly, an aliphatic or aromatic diisocyanate, such as, but not limited to an aromatic

diisocyanate, like MDI, or an aliphatic isocyanate, such as trimerized HDI (hexamethyl diisocyanate) or trimerized IPDI (isophenyl diisocyanate), or other acceptable diisocyanates or prepolymers which will react with the hydroxyl groups in the acrylic monomer. The compound, pentaerythritol triacrylate is a commercial product known as SR 444 of Sartomer Company, Inc. of Exton, Pennsylvania.

The prepolymer is added to an unsaturated resin composition, either alone or preferably in the concentrate form, known to contain some styrene monomer for viscosity control purposes, and thereby needing a reduction of the styrene monomer employed in the unsaturated polyester resin. The total amount of styrene monomer in the unsaturated resin composition would be less than 30% by weight. The prepolymer concentrate would also generally contain an inhibiting agent to provide for storage stability of the liquid concentrate, such as to maintain at least two-weeks' stability at 120°F, and which inhibitor generally comprises a quinone compound, such as parabenzoquinone.

The prepolymer concentrate is employed as an additive diluent to unsaturated polyester resin compositions, such as those unsaturated resin compositions, but not limited to, polyester resins prepared by reacting dicyclopentadiene (DCPD) with orthophthalic and maleic acid, the reaction of propylene glycol with maleic acid anhydride; and the reaction of isophthalic acid-maleic anhydride with neopentyl glycol, or other known unsaturated polyester resin compositions.

Generally, the unsaturated resin compositions contain an inhibitor to prevent prereaction until a promoter or catalyst is added to effect cure in the polyester resin after the addition of the prepolymer concentrate. The unsaturated polyester resin compositions contain a monomer for cross linking therewith, such as a diluent styrene monomer at reduced levels, where a concentrate prepolymer is employed. A cure is effected by employing an organic peroxide compound, and typically a metal salt, such as a

fatty acid salt, like a cobalt octoate or potassium octoate, is employed in combination with an organic ketone, such as methyl ethyl ketone peroxide, to provide for an exothermic curing reaction. The promoter and catalyst composition may also contain amide-type compounds for acceleration purposes, such as the dimethyl acetamide. Generally, the peroxide, metal salts, amines and amides are employed at low levels with the peroxide employed from about 0.1% to 2.5% by weight and the metal salts ranging from about 0.05% to 0.5% by weight and the amine or amide from about 0.05% to about 0.5% by weight. It has been found that after addition of the concentrate prepolymer to the unsaturated polyester resin composition used to prepare laminates, that the roll-out time was reduced, for example, to less than five minutes. The polyester resin composition without the concentrate prepolymer, even though such composition gelled in ten minutes, tended to stay rubbery for five minutes or more until a peak exotherm occurred, while with the use of the concentrate prepolymer, cure of the polyester resins to a rigid physical condition occurred in less than five minutes.

It has been found that the employment of the prepolymer concentrate of the invention helps in reducing roll-out where the unsaturated resin composition is employed with fiberglass, such as in a spray or mold operation, so that in the preparation of cured polyester fiberglass laminates with the use of the liquid concentrate prepolymer, no rolling of the concentrate was required when the concentrate was employed. Further, it has been noted that the polyester resin systems, with the liquid prepolymer concentrate added thereto, had little or no styrene monomer smell within three to four minutes after the spraying of the resin composition, which is believed to occur as a result of the cross linking taking place and tying up the styrene monomer.

The invention will be described for the purposes of illustration only in connection with certain embodiments; however, it is recognized that those persons skilled in the art may make various modifications, changes, additions and

improvements to the illustrated embodiments, without departing from the spirit and scope of the invention.

Embodiments of the Invention

Example 1

5 A liquid concentrate prepolymer prepared by admixing together 500 parts per weight of pentaerythritol triacrylate (acrylate SR-444) and 100 parts per weight of MDI (Papi 94, a trademark of Dow Chemical Company) and slowly reacted together without the present of catalyst to provide a liquid
10 pentaerythritol acrylic urethane. Four hundred parts per weight of a styrene monomer were added to the liquid prepolymer and together with 50 ppm of an inhibitor, parabenzoquinone. Employment of straight uretonomini-isocyanate (like Dow L143) and polymeric MDI (like Papi 27)
15 were also employed with the acrylate SR-444. Prepolymer solidification took place while heating the mixture in the oven. Low functionality hydroxyl-containing acrylic acrylates were tried employing diisocyanates of Papi-94 (Dow L143 and Papi 27); however, all these low functionality
20 monomers solidified when the prepolymers were made.

Example 2

 The liquid prepolymer concentrate was added to different types of unsaturated polyester resins, such as a general purpose orthophthalic resin containing 30% styrene
25 monomer and NPG orthoresin containing 30% styrene monomer, an NPG isophthalic resin containing 30% styrene monomer and DCPD ortho resin blends containing 30% styrene monomer. The unsaturated resin composition contained 50 ppm of an hydroquinone inhibitor with the mixing in of the liquid
30 prepolymer concentrate, catalysts and promoters were admixed as follows: 2% catalyst of methyl ethyl ketone peroxide (containing 9% oxygen); 0.2 parts per weight of 12% cobalt octoate as a promoter; 0.2 parts per weight of dimethyl acetyl acetamide (DMAA); and 0.1 parts per weight of
35 potassium octoate (15%). Ten percent of the liquid prepolymer concentrate was added to each resin. Gel time without the concentrate was about 10 minutes, while with the

concentrate added, gel time was reduced to 2.5 to 2.8 minutes. All samples prepared without the concentrate, even though they gelled in ten minutes, stayed rubbery for five minutes until a peak exotherm occurred, while the same polyester resin samples with the 10% liquid prepolymer concentrate became rigid in less than five minutes.

Example 3

The unsaturated polyester resin samples containing the 10% liquid prepolymer concentrate were put on a Binks B-8 fiberglass spray machine and sprayed with a Binks Century gun with external mix catalyst above and the fiberglass at about 22% by weight was sprayed at 3/4 inch fiber length employing a four by four foot plate mold. With each unsaturated polyester resin system used without the liquid prepolymer concentrate on the surface, the glass required rolling to make an acceptable laminate without air. The liquid prepolymer concentrate added at 10% and sprayed provided for a fiberglass polyester cured laminate requiring no roll out. Further, the resin systems with the liquid concentrate had no styrene monomer smell within three to four minutes of spraying of the polyester resin as a result of cross linking taking place with the styrene monomer.

Physical testing was done on all the polyester resin compositions, with or without the liquid prepolymer concentrate as added at 10%, and the test results are shown on the accompanying Table II.

Example 4

Compression-molded fiberglass trays were prepared employing an isophthalic polyester resin with a heat-activated catalyst, such as tertiary butyl perbenzoate, and added to a 33% glass fiber mat, with mold temperatures at 280°F., a cycle time of 90 seconds and with 10% of the liquid prepolymer concentrate added to the polyester resin. Upon addition of the liquid prepolymer concentrate, cycle times for curing were reduced to 60 seconds. The glass fiber wet-out was improved, styrene emissions were reduced

and the laminate had improved physical properties and chemical resistance.

Example 5

Further tests were carried out with other polyester resins with and without a styrene monomer added and to which 10% by weight of the liquid concentrate of Example 1 was added. The cycle times of the polyester resin increased to 10 to 12 minutes on all types of polyester resins, and when each polyester resin system was sprayed with the fiberglass, no improvement was seen over the same polyester resin without the presence of the liquid prepolymer concentrate of the invention.

Urethane Oligomers

Aliphatic urethane acrylate and 2-(2 Ethoxyethoxy) Ethyl acrylate ester (Craynor 961-H)

Epoxy acrylate oligomer plus 1, 6 Hexanediol diacrylate ester (Craynor 120 B)

Aromatic urethane oligomer plus 1, 6 Hexanediol diacrylate ester (Craynor 970)

Example 6

In the marine and bathtub industry in the preparation of fiberglass laminate, water absorption is critical to the success of the end product. Extensive boiling tests were run on samples of polyester resins of DCPD, G.P.-Ortho, NPG-Ortho and NPG-Iso polyester resins, both with and without the liquid prepolymer concentrate added. The following Table III shows the percent water absorption at 80°C for 160 hours.

TABLE III

	Type Resin							
	<u>DCPD</u>	<u>DCPD+C*</u>	<u>PG</u>	<u>PG+C</u>	<u>NPG-Ortho</u>	<u>+C</u>	<u>NPG - ISO</u>	<u>+C</u>
% H ₂ O Absorption	3.2	1.6	3.1	1.4	2.9	1.4	2.0	1.2

*C = 10% concentrate made from SR-444.

The above results indicate that all unsaturated polyester resin compositions showed significant improvement in water

absorption when the liquid prepolymer concentrate was added at a level of 10% parts by weight.

Thus, the modified prepolymer concentrate prepared by the employment of pentaerythritol triacrylate, MDI and a styrene monomer with an inhibitor when added to unsaturated polyester resin compositions results in improvement in the physical and chemical properties, such as decrease in cure time, reduction in styrene emissions, reduction in styrene odor when sprayed, reduction in roll-out of molded or sprayed laminates, reduction in water absorption, increased chemical resistance, higher heat distortion temperatures and higher impact strength.

The unsaturated polyester resin composition with the modified acrylic-urethane prepolymer or oligomer and with a styrene monomer of less than about 30% by weight may be cured with a methyl ethyl ketone peroxide (1.5%-2.0%) and a cobalt salt (0.1%-0.5%). The composition can be sprayed as a glass-fiber barrier coat behind a polyester or polyester-acrylic gel coat with a very fast cure time and with rapid cure. The barrier coat strengthens the gel coat and reduces water absorption and lowers water and vapor transmission. The composition may be sprayed or used with charged glass fibers in an open or closed mold, so that a no-roll surface without air entrapment can be prepared. After the gel coat is applied and a barrier coat is added (prior to resin and glass application), no glass fibers are visible on the gel coat side, eliminating veil mats, to provide a class A finish where a class A mold is used.

CLAIMS

What is claimed is:

Claim 1. A modified acrylic-urethane prepolymer composition adapted for addition to unsaturated polyester resins to improve cured resin properties, which prepolymer composition comprises:

- a) an acrylic-urethane prepolymer prepared by the reaction of a diisocyanate with an hydroxyl-containing acrylate monomer;
- b) a styrene monomer; and
- c) an inhibitor in an amount to retard the reaction of the prepolymer and the styrene monomer.

Claim 2. The composition of claim 1 wherein the acrylate monomer comprises a poly hydroxy C₂-C₆ alkyl polyacrylic acid monomer.

Claim 3. The composition of claim 2 wherein the acrylate monomer comprises a pentaerythritol polyacrylate.

Claim 4. The composition of claim 3 wherein the acrylate monomer comprises a pentaerythritol triacrylate.

Claim 5. The composition of claim 1 wherein the inhibitor comprises an inhibiting amount of a quinone compound.

Claim 6. The composition of claim 1 which contains from about 5% to 40% by weight of the styrene monomer.

Claim 7. The composition of claim 1 wherein the acrylate monomer comprises a hydroxy C₂-C₃ methacrylate or acrylate monomer.

Claim 8. The composition of claim 4 wherein the diisocyanate comprises MDI.

Claim 9. The composition of claim 4 wherein the styrene monomer comprises less than 30% by weight.

Claim 10. An unsaturated polyester resin composition to which has been added an amount from 5 to 30 weight percent of the prepolymer composition of claim 1.

Claim 11. The cured resin composition of claim 10 which includes a cross-linking amount of a peroxide compound.

Claim 12. The composition of claim 1 wherein the
2 acrylate monomer comprises an ethoxylated or propoxylated
trimethylol propane polyacrylate.

Claim 13. The cured resin composition of claim 11
2 which includes a cross-linking promoting amount of a metal
salt.

Claim 14. The cured resin composition of claim 10
2 which comprises a cured laminate of the composition, the
laminate containing glass fibers or particulate filler
4 material.

Claim 15. The cured resin composition of claim 10 which
2 includes a cross linked styrene monomer of less than about
30% by weight of the cured polyester resin.

Claim 16. The cured resin composition of claim 10 which
2 includes from about 5% to 30% by weight of the prepolymer
composition of claim 1.

Claim 17. A modified acrylic urethane prepolymer
2 composition adapted for addition to an unsaturated polyester
resin composition, which prepolymer composition comprises:

4 a) an acrylic urethane prepolymer prepared by the
reaction of MDI with a high functionality hydroxy-
6 containing alkyl polyacrylate;

b) from about 0% to 40% by weight of a styrene
8 monomer; and

c) a quinone inhibitor in an amount to retard the
10 reaction of the prepolymer and the styrene monomer.

Claim 18. An unsaturated polyester resin composition to
2 which has been added up to 50% by weight of the prepolymer
composition of claim 17.

Claim 19. The cured resin composition of claim 18 and
2 which cured resin composition contains from 0% to 30% by
weight of glass fibers.

Claim 20. A method of preparing an unsaturated resin
2 composition with improved properties and which method
comprises:

4 adding to an unsaturated resin composition a cross
linking amount of a modified acrylic urethane

6 prepolymer composition, which prepolymer
composition comprises an acrylic-urethane
8 prepolymer prepared by the reaction of a
diisocyanate with an hydroxyl-containing acrylate
10 monomer and curing the unsaturated resin
composition.

Claim 21. The method of claim 20 which includes
2 preparing a cured fiberglass laminate of the unsaturated
resin composition.

Claim 22. The method of claim 20 wherein the
2 unsaturated resin composition has a styrene monomer in an
amount of less than about 30% by weight.

Claim 23. The method of claim 20 wherein the acrylate
2 monomer comprises a pentaerythritol triacrylate, and the
diisocyanate comprises MDI.

Claim 24. The method of claim 20 wherein the prepolymer
2 comprises from about 5% to 30% by weight of the polyester
resin composition.

Claim 25. The method of claim 20 which includes
2 spraying a mixture of the polyester resin composition
containing the prepolymer composition and a styrene monomer
4 with fiberglass to form a cured polyester resin-fiberglass
laminate.

Claim 26. The cured polyester resin prepared by the
2 method of claim 20.

Claim 27. A prepolymer suitable for use for addition to
2 an unsaturated polyester resin composition, which prepolymer
comprises a liquid acrylate-urethane compound prepared by
4 the reaction of pentaerythritol polyacrylate with about a
stoichiometric or slight excess amount of MDI.

Claim 28. A promoted unsaturated polyester resin
2 composition containing a styrene monomer to which has been
added a cross linking diluent amount of the prepolymer of
4 claim 27.

AMENDED CLAIMS

[received by the International Bureau on 08 September 1997 (08.09.97);
original claims 17, 27 and 28 cancelled;
original claims 1-3, 7-9 and 12 amended;
new claims 29 and 30 added; remaining claims unchanged (4 pages)]

Claim 1. A modified liquid acrylic-urethane prepolymer
2 concentrate composition adapted for addition to a curable
unsaturated polyester resin to improve cured resin
4 properties as a diluent additive and to provide a polyester
resin with reduced styrene content, which prepolymer
6 composition consists essentially of:

a) a liquid acrylic-urethane prepolymer prepared by
8 the reaction of a diisocyanate in a stoichiometric or
greater amount with a high functionality polyhydroxyl-
10 containing acrylate monomer;

b) a diluent styrene monomer; and

12 c) an inhibitor in an amount to retard the reaction of
the prepolymer and the styrene monomer.

Claim 2. The composition of claim 1 wherein the
2 acrylate monomer comprises a poly hydroxy C₂-C₆ alkyl
acrylate.

Claim 3. The composition of claim 1 wherein the
2 acrylate monomer comprises a pentaerythritol polyacrylate.

Claim 4. The composition of claim 3 wherein the
2 acrylate monomer comprises a pentaerythritol triacrylate.

Claim 5. The composition of claim 1 wherein the
2 inhibitor comprises an inhibiting amount of a quinone
compound.

Claim 6. The composition of claim 1 which contains
2 from about 5% to 40% by weight of the styrene monomer.

Claim 7. The composition of claim 1 wherein the
2 acrylate monomer comprises a polyhydroxy C₂-C₃ methacrylate
or acrylate monomer.

Claim 8. The composition of claim 4 wherein the
2 diisocyanate comprises MDI or polymeric MDI.

Claim 9. The composition of claim 4 wherein the styrene
2 monomer comprises less than 30% by weight of the unsaturated
resin to which the composition is to be added.

Claim 10. An unsaturated polyester resin composition
2 to which has been added an amount from 5 to 30 weight
percent of the prepolymer composition of claim 1.

2 **Claim 11.** The cured resin composition of claim 10
which includes a cross-linking amount of a peroxide
compound.

2 **Claim 12.** The composition of claim 1 wherein the
acrylate monomer comprises an ethoxylated or propoxylated
trimethylol propane or glycerol polyacrylate.

2 **Claim 13.** The cured resin composition of claim 11
which includes a cross-linking promoting amount of a metal
salt.

2 **Claim 14.** The cured resin composition of claim 10
which comprises a cured laminate of the composition, the
laminate containing glass fibers or particulate filler
4 material.

2 **Claim 15.** The cured resin composition of claim 10 which
includes a cross linked styrene monomer of less than about
30% by weight of the cured polyester resin.

2 **Claim 16.** The cured resin composition of claim 10 which
includes from about 5% to 30% by weight of the prepolymer
composition of claim 1.

2 **Claim 18.** An unsaturated polyester resin composition
which has been added up to 50% by weight of the prepolymer
composition of claim 17.

2 **Claim 19.** The cured resin composition of claim 18 and
which cured resin composition contains from 0% to 30% by
weight of glass fibers.

2 **Claim 20.** A method of preparing an unsaturated resin
composition with improved properties and which method
comprises:

4 adding to an unsaturated resin composition a cross
linking amount of a modified acrylic urethane
6 prepolymer composition, which prepolymer
composition comprises an acrylic-urethane
8 prepolymer prepared by the reaction of a
diisocyanate with an hydroxyl-containing acrylate
10 monomer and curing the unsaturated resin
composition.

2 **Claim 21.** The method of claim 20 which includes
preparing a cured fiberglass laminate of the unsaturated
resin composition.

2 **Claim 22.** The method of claim 20 wherein the
unsaturated resin composition has a styrene monomer in an
amount of less than about 30% by weight.

2 **Claim 23.** The method of claim 20 wherein the acrylate
monomer comprises a pentaerythritol triacrylate, and the
diisocyanate comprises MDI.

2 **Claim 24.** The method of claim 20 wherein the prepolymer
comprises from about 5% to 30% by weight of the polyester
resin composition.

2 **Claim 25.** The method of claim 20 which includes
spraying a mixture of the polyester resin composition
containing the prepolymer composition and a styrene monomer
4 with fiberglass to form a cured polyester resin-fiberglass
laminate.

2 **Claim 26.** The cured polyester resin prepared by the
method of claim 20.

4 **Claim 29.** The method of claim 20 which includes curing
the resin composition employing an organic peroxide curing
agent.

2 **Claim 30.** A modified liquid acrylic-urethane
prepolymer concentrate composition adapted as a diluent
additive to a curable unsaturated polyester resin to improve
4 the cured resin properties, and to provide a curable
unsaturated polyester resin with a styrene monomer content
6 of less than 40% by weight of a styrene monomer, which
liquid concentrate composition consists essentially of:

8 a) a liquid acrylic-urethane prepolymer prepared by
the reaction of a MDI or a MDI polymer with a high
10 functionality polyhydroxyl acrylate monomer selected from
the group consisting of a pentaerythritol polyacrylate and
12 a ethoxylated or propoxylated alkyl acrylate, the MDI or MDI
polymer present in a stoichiometric amount or a slight
14 excess amount;

b) a diluent amount of a styrene monomer which would
16 comprise less than about 40% by weight of the curable
polyester resin to which the concentrate composition is to
18 be added; and

c) an inhibitor in an amount to retard the reaction of
20 the prepolymer and the styrene monomer prior to addition to
the polyester resin.

STATEMENT UNDER ARTICLE 19

Applicant has amended the claims of Group I to close the claim. The claims of Group II and III are directed to unsaturated polyester resin compositions and method containing the liquid prepolymer additive composition. None of the references teach or suggest the inventions of Groups I, II or III.

The Kansai Paint KK application (partial English language translation of examples enclosed) relates to oxidative curing polymer aqueous emulsion and is directed to per se curable compositions and not Applicant's additive non-cured prepolymer composition (I) and not to unsaturated resin composition and methods. The Kansai application must include a polymerization initiator and does not use a styrene nor a peroxide curing agent with an unsaturated resin composition.

The Osborn patent is directed to a radiation curable urethane composition and not an additive non-curable prepolymer with styrene (I) and is not directed to the unsaturated resin composition and method with the prepolymer and cured by a peroxide (II and III).

The Wang et al patent relates to wholly different polymers and merely states that styrene can increase rigidity.

The Hudak patent does not concern an additive prepolymer (I) and relates to polyester resins with urethane linkages. However, the Hudak polyester resins are not directed to the problem of reduced styrene content and the advantages thereof, but to specific polyester-urethane resins.

The Den Hartog et al patent does not relate to Applicant's additive prepolymer (I) or to the unsaturated polyester resins and method employing the additive (II and III). The Den Hartog et al patent concerns water based coating compositions of amide acrylic polymers and polyurethanes.

Acceptance of these amendments is respectfully requested.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US97/05900

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : C08F 2/22; C08L 101/02; C09D 5/02

US CL : Please See Extra Sheet.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 526/301; 525/520, 440, 443, 445, 455, 456, 518

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X ---- Y	Database WPAT on ORBIT, week 8915, London: Derwent Publications Ltd., AN 81-038745D/22, Class A82, J89015540 B (KANSAI PAINT), abstract.	1-10, 12, 17, 18 ----- 11, 13-16, 19-26
Y	US 4,192,762 A (OSBORN) 11 March 1980, columns 2-5.	1-26
Y,P	US 5,599,877 A (WANG et al.) 04 February 1997, columns 4-17.	1-26
Y	US 5,006,413 A (DEN HARTOG et al.) 09 April 1991, columns 2-7.	1-26
Y	US 3,882,189 A (HUDAK) 06 May 1975, columns 2-9.	1-26



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:	* T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
* A* document defining the general state of the art which is not considered to be of particular relevance	* X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
* E* earlier document published on or after the international filing date	* Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
* I* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	* &*	document member of the same patent family
* O* document referring to an oral disclosure, use, exhibition or other means		
* P* document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

27 MAY 1997

Date of mailing of the international search report

08.07.97

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

JEFFREY T. SMITH

Telephone No. (703) 308-2351

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US97/05900

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This international report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:

3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

Please See Extra Sheet.

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☒ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
1-26
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US97/05900

A. CLASSIFICATION OF SUBJECT MATTER:

US CL :

526/301; 524/ 501, 507; 525/520, 440, 443, 445, 455, 456, 518; 428/423.1, 441.

BOX II. OBSERVATIONS WHERE UNITY OF INVENTION WAS LACKING

This ISA found multiple inventions as follows:

This application contains the following inventions or groups of inventions which are not so linked as to form a single inventive concept under PCT Rule 13.1.

Group I, claim(s) 1-10, 12, 17, 18, and 20-26, drawn to composition of acrylic-urethane prepolymer, styrene monomer and polymerization inhibitor.

Group II, claim(s) 11, 13, 15, 16, and 19, drawn to cured composition.

Group III, claim(s) 14, drawn to multi-layered laminate.

Group IV, claim 27, drawn to the reaction product of an acrylic-urethane compound and MDI.

Group V, claim 28, drawn to the reaction product of an acrylic-urethane compound, MDI, and styrene monomer.

The inventions listed as Groups II-V do not relate to a single inventive concept under PCT Rule 13.1 because, under PCT Rule 13.2, they lack the same or corresponding special technical features for the following reasons: The special technical feature of Group I is the admixed acrylic-urethane prepolymer, styrene monomer and polymerization inhibitor. The composition is not reacted which is exemplified by the presence of the polymerization inhibitor.

Group II does not include special technical feature of Group I because Group II upon curing is not separable or identifiable by its component parts due to the chemical crosslinking which occurs.

Group III does not include special technical feature of Group I because Group III is a multi-layered laminate which includes solid cured resins and glass fibers. The special technical feature of the laminate is the combination of layers.

Group IV does not include special technical feature of Group I because Group IV does not include an inhibitor and styrene which are required for the special technical feature of Group I.

Group V does not include special technical feature of Group I because Group V does not include an inhibitor which is required for the special technical feature of Group I.